

* PRODUCT INFORMATION *

HUSKEY™ HTL-4000 PTFE GREASE (Product Code 46600)

DESCRIPTION

HUSKEY HTL-4000 PTFE GREASE represents some of the most advanced lubricant technology. It is a premium-quality synthetic oil thickened with PTFE. It is blended with state-of-the-art additives to provide maximum equipment protection in extremely high and low temperatures (Operating Range -65° to 500°F). **HUSKEY HTL-4000 PTFE GREASE** also meets the requirements of NSF/ U.S.D.A. H-1, which after approval gives it full acceptability in areas where incidental food contact may occur.

USAGE

HUSKEY HTL-4000 PTFE GREASE is truly a multi-service lubricant for extended service under extreme high and low conditions. **HUSKEY HTL-4000 PTFE GREASE** has proven to be a problem solving product in a wide variety of industries and applications. Some such applications include: Freezer bearings, oven bearings and chains, pumps, kilns, conveyors, etc.

ADVANTAGES

- MEETS NSF/ U.S.D.A. H-1 REQUIREMENTS
- NON-STAINING
- WATER, FROST AND STEAM RESISTANT
- WIDE TEMPERATURE RANGE
- THICKENED WITH PTFE
- EXCELLENT ANTI-WEAR AND EP CAPABILITIES
- NON-MELTING

PACKAGE AVAILABILITY

1 gal. Pails, 5 gal. Pails, 15 gal. Kegs, and 55 gal. Drums



HUSKEY Specialty Lubricants

manufactured by HUSK-ITT Corporation / SPECIALTY LUBRICANTS Corporation

Western Region Office:

1580 Industrial Avenue, Norco, California 92860
(951) 340-4000 • Fax: (951) 340-4011
(888) 4-HUSKEY • www.huskey.com

Eastern Region Office:

8300 Corporate Park Drive, Macedonia, Ohio 44056
(330) 425-2567 • Fax: (330) 425-9637
(800) 238-LUBE

* PRODUCT INFORMATION *

TYPICAL PROPERTIES

DESCRIPTION

HUSKEY Product:	HTL-4000 PTFE Grease
Color:	Translucent White
Base Oil:	Synthetic
Thickener:	Sub-Micron Size PTFE
Texture:	Buttery
Solid Lubricant:	Sub-Micron Size PTFE

TESTS

ASTM TEST METHOD

RESULTS

N.L.G.I. Grade	-----	2
Worked Penetration	D-217	
60 Strokes		265
10,000 Strokes		295
Base Oil Viscosity,		
cSt @ 40°C	D-445	65
cSt @ 100°C		9.6
Pour Point, °F	D-97	-65
Flash Point, °F	D-92	507
Dropping Point °F	D-566	None
Oil Separation, % Loss	D-1742	0.0
Corrosion Preventative Test	D-1743	PASS
Four Ball Wear Scar, mm		
(40 Kg. 1 hr. @ 1200 rpm, 75°C)	D-2266	0.6

The name of this product or group of products is for product identification purpose only. HUSK-ITT Corporation / SPECIALTY LUBRICANTS Corporation makes no warranties, representations or conditions of any kind express or implied, whether for merchantability or fitness for use with respect to these products. The final determination of the suitability of the products for the application contemplated by the user is the sole responsibility of the buyer. HUSK-ITT Corporation / SPECIALTY LUBRICANTS Corporation sales personnel are not authorized to amend this warranty limitation. 06/11



HUSKEY Specialty Lubricants

manufactured by HUSK-ITT Corporation / SPECIALTY LUBRICANTS Corporation

Western Region Office:
 1580 Industrial Avenue, Norco, California 92860
 (951) 340-4000 • Fax: (951) 340-4011
 (888) 4-HUSKEY • www.huskey.com

Eastern Region Office:
 8300 Corporate Park Drive, Macedonia, Ohio 44056
 (330) 425-2567 • Fax: (330) 425-9637
 (800) 238-LUBE